



## Flake Capping Compound to ASTM C617 22Kg

Code: 34-6100

Product Group: Sulphur Compound Method, Flake  
Capping Compound

Supplied in 22 kg box.

### Standards

ASTM C617, AASHTO T231

### Specification

Density	13.7 lbs./cu. ft. (2,186 kg/cu. m.).
Tensile Strength	605 psi (4.2 x 10 <sup>5</sup> kg/sq m.) after 48 hrs.
Compressive Strength	5,000 psi (3.6 x 10 <sup>6</sup> kg/sq m.) minimum, after 2 hrs.
Melting Range	23 °-24 °F (11 °-115 °C).
Optimum Pouring Range	260°-290°F (126°-143 °C).
Weight	Net 50 lbs. (22.7 kg); Shpg. 52 lbs. (23.6 kg).

### Accessories



#### 6" Retaining Caps

Code: 34-6134

### Alternatives



#### 6" Retaining Caps

Code: 34-6134